

## TECHNICAL BULLETIN #4



Thuja plicata

Western Red Cedar

# **Cedar Siding:**Grades, Seasoning, Patterns & Textures

Wood siding is one of the most versatile of all materials that can be installed as exterior siding due in part to its ability to accept a variety of finishes. This opens the door to unlimited possibilities of color choices and appearances.

### Grades

One of the most popular species of wood siding is Western Red Cedar because it has dimensional stability, holds finishes extremely well and is naturally durable. Western Red Cedar grades can be generally categorized into clear grades and knotty grades.

Clear, premium grades have few adverse characteristics (knots, splits) etc. For bevel or clapboard siding, the highest grade available is *Clear VG Heart* (VG stands for vertical grain) followed by *A Bevel*. For all other patterns, cedar may be found in a variety of premium grades, including *Clear Heart*, *A Grade*, *B & Better Select* and *C & Better Select*. Because of

their superior quality and appearance, the clear grades are generally more expensive and less common than the knotty grades.

Knotty grades have larger, more frequent knots and other characteristics. #2 Common, #3 Common, Select Knotty and Quality Knotty are recognized agency grades that are available. The grade of cedar used may influence finish selection. Clear grades accept paint, stain or water repellents easily, while stains or water repellents are recommended for coating knotty grades.

# **Seasoning**

Cedar siding can be purchased as unseasoned (green), 19% maximum moisture content (S-dry), or 15% maximum moisture content (MC15). Typically, the clear grades are kiln dried to MC15 specifications, while knotty grades are normally sold as S-Dry or green. If unseasoned siding is purchased, it must be allowed to dry for 30 days prior to finishing and installation, while dry sidings should shrink less and can be finished immediately.

Moisture content should be below 15% prior to application of a finish, allowing it to penetrate and dry properly. Stains or water repellents do not form films like paints and are therefore preferred when siding must be finished prior to being allowed to dry completely.

#### **Patterns**

Cedar siding is available in a variety of patterns with bevel or clapboard being the most common. *Channel rustic, shiplap* and *tongue & groove* patterns are also popular. Installation differs for each, and each has applications for which it is best suited. Bevel patterns can only be installed horizontally, but they are more forgiving when it comes to shrinkage. Channel rustic, tongue & groove and shiplap patterns can be installed either horizontally or vertically, but some require close attention to detail and seasoning. As a rule, the narrower and thicker the pattern, the better the performance.

## **Textures**

Siding is available in smooth, rough or saw-textured surfaces. When used with clear or semi-transparent finishes, a smooth surface will show the grain patterns and color variations in the wood more than other textures. These surfaces

# **Cedar Siding** (Continued from front)

also absorb less finish and typically require more maintenance than other textures. In contrast, rough and saw-textured surfaces can absorb about twice as much finish as smooth-textured surfaces and, when protected by stain- and water-repellent finishes, need to be recoated much less frequently.

Wood siding and wood finishes go hand in hand in providing consumers with virtually unlimited choices for appearance. By properly selecting the grade, seasoning, pattern and texture of the siding and by protecting it from moisture, sun and mold with a quality finish, wood siding can last for many decades.

#### **SIDING GRADES**

General Categories Notations Translations Translations		GRADES			Grade Rule Paragraph Numbers for		
		Western Species		Cedar	Reference & Specifying		
		Selects <sup>1</sup>	Finish	Western & Canadian	WWPA <sup>2</sup>	WCLIB <sup>3</sup>	NLGA <sup>4</sup>
ALL PATTERNS	PREMIUM	C Select D Select	Yasese Peng	Clear Heart* A Grade*	2011 2012 2013 2013 2013 2013	902 1 0 5 107 E	200 i 2000 2000
Additional Grades for Bevel Patterns	Premiem		Summer Proof	Clear VS Heart A Bevel B Book Door C Book	51.0 51.0 51.0 51.0	100 kg 100 h 106 : 106 :	2074 (975) (47 (40) (40) (20%)
	Knotty		Translation	Select Knotty Quality Knotty	50		297 na 2007 a
ALL PATTERNS	KNÓTTY GRADES	Common	Appropria				
		≠2 Common	Sister Grand Charlest Torr	Seleci Knotly	3017	nav ma	614g (914g
		#3 Commen		Quality Knoffy*	40.5	1,	Phil. 2040
		Common	Standard		0014	":1.	4.

Equivaent grades under the some temporal habitance in WMD/PL (solvies a labor tribuno).

Information courtesy of WWPA, "Specifying Lumber" 1613/A-2/Rev. 10-92

Information in this Technical Bulletin was provided by Jeff Fantozzi, Western Wood Products Association.



#### Cabot®

Newburyport, MA 01950 Tel.: 800-US-STAIN Fax: 1-800-998-3299

Visit the Cabot Home Page at: cabotstain.com

The view of the bound of the control of the property of the control of the contro

nsyntyngt og dylagtigning fatt grunn i hteksiska filled i thersking. Trolik dets usen minkering men i 1913 i skammens des intres vilgen blikk om olide ochtendts, erd.

Quality Birbly, present STK is a propositivy designative and shoot in AuSC abdroxibility son-The grade names in bold face type are the most widely evailable grades. There we offe age for an increase occurs on the court name and in the court name of a characteristic occurs on the court name of a characteristic occurs on the court name of sales.