



TECHNICAL DATA

TEAK OIL FINISH #8098 CLEAR FINISH

DESCRIPTION

Recommended Uses:

Cabot Teak Oil Finish restores and maintains teak wood with its premium blend of natural ingredients. Teak Oil provides a rich oiled appearance while preventing graying and staining. This deep-penetrating formula extends the life of teak by replacing the natural oils taken away by exposure to the elements. This clear finish resists cracking or peeling and accentuates the natural beauty of teak. Ideal for marine environments.

Do not apply over varnish, as it cannot penetrate the wood properly.

This product is superior protection for hardwoods – ideal for teak, mahogany and rosewood.

Composition:

Tung and linseed oils

Finish:

This product has a clear finish

Tinting/Intermixing:

Cabot Teak Oil Finish cannot be tinted or intermixed with any other Cabot product.

Coverage/Thinning:

One quart covers up to 50-100 sq. ft. (4.6-9.3 m²) depending upon wood porosity. Do not thin.

Packaging/Containers:

Available in quart containers.

Restrictions:

DO NOT USE OVER PRODUCTS THAT CONTAIN STEARATES.

Do not apply when air or surface temperature is below 50°F.

Do not apply over wet or damp surfaces.

Do not thin or add colorant to this product.

Do not apply this product adjacent to cement or stucco. Do not use on decks or siding.

Cleanup and Disposal: Clean brushes and equipment with mineral spirits. Keep container closed when not in use. Do not transfer contents to other containers for storage or disposal. In case of spillage, absorb with inert material such as sand or kitty litter.

Dispose of empty cans or unused portion in accordance with local, state and federal regulations. Material Safety Data Sheets (MSDS) are available upon request.

DANGER: Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after each use, place rags, steel wool or waste in a sealed, water-filled metal container and dispose of according to local regulations.

Physical and Chemical Data:

Drying Time: 2-5 minutes, apply stain within 30 minutes.

Weight: 7.0+/-0.1 pounds per gallon.

Flash Point: 106°F (41°C)

Film Thickness: None because Cabot Teak Oil Finish penetrates into the wood, leaving no film build.

Shelf Life: A minimum of five (5) years in closed original containers.

% Solids (weight): 89 - 89.2

% Solids (volume): 88 - 89

% Pigment (weight): 0

Viscosity: 15-25 cps.

Pigment Type: N/A

Vehicle Type: Tung and linseed oils

Solvent Type: Aliphatic and Terpene Hydrocarbons

V.O.C. Content: GPL Maximum of 100 grams/liter (0.8 pounds/gallon)

TECHNICAL DATA

Environmental Impact:

These products are in compliance with V.O.C. (Volatile Organic Compounds) requirements for Specialty Architectural Coatings under current regulations. Call Cabot's Technical Services & Support for additional information pertaining to current V.O.C. rulings.

WARNING! VAPOR HARMFUL. COMBUSTIBLE LIQUID & VAPOR.

DANGER: CONTAINS PETROLEUM DISTILLATES. COMBUSTIBLE:

DO NOT SMOKE. Keep away from sparks, open flame, and lit cigarettes. Turn off stoves, heaters, electric motors, pilot lights and other sources of ignition during use and until all vapors are gone. Prevent build up of vapors by opening all windows and doors for cross ventilation.

**Emergency Medical Telephone:
1-888-345-5732**

TEAK OIL FINISH #8098 CLEAR FINISH

APPLICATION

Surface Preparation:

Remove any stains and oxidation by cleaning with an oxalic acid solution or commercial wood cleaner following the label directions. Rinse well and allow the teak to dry thoroughly before applying Teak Oil. If the teak was previously sealed with a film-forming finish such as varnish or polyurethane, the finish must be completely removed before using Teak Oil.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the USEPA/Lead Information Hotline at 1-800-424-LEAD (5323) or visit www.epa.gov/lead.

Application:

Apply liberally with a lint-free cloth, natural bristle brush or short nap roller working with the grain of the wood. After 10 minutes, remove any excess Teak Oil. Allow to dry 2-4 hours. Apply additional coats, as needed to rejuvenate wood, allowing for proper dry time between coats. Severely bleached or dried-out teak may require 4-6 coats of Teak Oil.

Drying Time: Dries to the touch in about 2 hours. Wait 2-4 hours before recoating. Dry times are longer in high humidity or cool temperatures. Apply only when surface and air temperatures are between 50-90°F (10-32°C) during application and drying time.

Number of Coats: Depending upon porosity of wood, apply as needed.

AVAILABILITY

Cabot Wood Care Products are sold throughout the United States and Canada. For a list of Cabot dealer locations, please contact Cabot's Technical Services & Support at 1-800-US-STAIN.

WARRANTY

If this product does not perform as stated on the label after you apply it according to label directions, Cabot will either replace this product or refund its purchase price, at its option. Cabot disclaims all other implied or expressed warranties. Cabot will not provide or pay for labor for removal or application of the product. This warranty excludes all incidental or consequential damages. This warranty gives you specific legal rights, and you may have other rights which vary from state to state.

MAINTENANCE

Minimal because Cabot Teak Oil penetrates deep into the wood.

TECHNICAL SERVICES

For additional technical information see your specialized Cabot dealer or call Cabot's Technical Services & Support toll-free at 1-800-US-STAIN (877-8246).

FILING SYSTEMS

For complete model specifications and technical data on all Cabot products, visit the Cabot Home Page at: cabotstain.com.



Cabot®
Newburyport, MA 01950
Tel.: 800-US-STAIN
Fax: 1-800-998-3299
cabotstain.com